

No. 170.

Treasury Department,

OFFICE OF THE DIRECTOR OF THE MINT,

Washington, D. C.,

January 17, 1887.

Sir:

I transmit herewith the Assayer's report upon special assay coins
and two subsequent
taken from the first deliveries in each week at your Mint during the
Month of October, 1886, and forwarded for test as prescribed
by the Regulations.

The coins were found to be within the legal limits of tolerance.

Very respectfully,

James B. Smith
Director.

Superintendent Mint U. S.,


At Philadelphia, Pa.

50

Treasury L. S.
Washington D. C.
Jan. 12. 1887.

James. D. Kimball.
Director.

Transmits Assayers Report
upon Special Assay Coins
taken from first & two
Subsequent Deliveries
October 1886.



Treasury Department,

BUREAU OF THE MINT,

Washington, D. C., *July. 12th*, 1887.

Assayer's Report of Test Coins, issued at the Mint of the
U. S. at *Philadelphia*, in *Oct.*, 1886:

DENOMINATION.	No. of Delivery.	WEIGHT.		FINENESS.	
		GRAINS.	DEC.	GOLD.	SILVER.
Double Eagle ...	212	411	80		900 4
	215	412	40		900 1
Eagle	217	412	55		900 4
	220	411	95		900 1
Half Eagle	224	412	27		900 4
	227	412	23		900 4
Three Dollars ...	229	413	05		900 2
	234	412	44		900 1
Quarter Eagle...	236	413	03		899 6
	238	412	57		899 7
Standard Dollar.	241	412	75		899 9
	244	412	40		900 4
Half Dollar	246	412	67		899 8
Quarter Dollar					
<i>Average weight</i>		442	43 1		
<i>Average fineness</i>					900 11

W. P. Lawrence

Assayer.

2

Treasury Department,

BUREAU OF THE MINT,

Washington, D. C., *Jan 12*, 1887.Assayer's Report of Test Coins, issued at the Mint of the
U. S. at *Philadelphia*, in *Oct.*, 1886:

DENOMINATION.	No. of Delivery.	WEIGHT.		FINENESS.	
		GRAINS.	DEC.	GOLD.	SILVER.
Double Eagle ...	214	38	57	}	9002
Eagle		38	20		
Half Eagle.....		38	63		
Three Dollars ...		38	78		
Quarter Eagle...		38	98		
One Dollar		38	74		
Standard Dollar.		38	65		
Half Dollar		40	08		
Quarter Dollar ..		39	03		
Dime					
Average weight		38	831		
			31		

W. P. Lawson

Assayer.

Treasury Department,

BUREAU OF THE MINT,

Washington, D. C., *Jan'y 12*, 188*7*.

Assayer's Report of Test Coins, issued at the Mint of the
U. S. at *Philadelphia*, in *Oct.*, 188*6*:

DENOMINATION.	No. of Delivery.	WEIGHT.		FINENESS.	
		GRAINS.	DEC.	GOLD.	SILVER.
Double Eagle ...	<i>Delivery No. 223</i>	<i>38 22</i>		<i>900.3</i>	
Eagle		<i>38 60</i>			
Half Eagle		<i>38 33</i>			
Three Dollars ...		<i>38 75</i>			
Quarter Eagle...		<i>38 02</i>			
One Dollar		<i>38 48</i>			
Standard Dollar.		<i>37 78</i>			
Half Dollar		<i>39 03</i>			
Quarter Dollar ..		<i>38 48</i>			
<i>Average weight</i>		<i>38 55</i>			
		<i>38 42 4</i>			

W. P. Lauen

Assayer.

4

Treasury Department,

BUREAU OF THE MINT,

Washington, D. C., *January 17* 188*7*.Assayer's Report of Test Coins, issued at the Mint of the
U. S. at *Philadelphia*, in *Oct*, 1886.

DENOMINATION.	No. of Delivery.	WEIGHT.		FINENESS.	
		GRAINS.	DEC.	GOLD.	SILVER.
Double Eagle ...	<i>Delivery No. 430</i>	<i>38 36</i>		<i>899.2</i>	
Eagle		<i>38 28</i>			
Half Eagle		<i>38 72</i>			
Three Dollars ...		<i>38 38</i>			
Quarter Eagle ...		<i>38 53</i>			
One Dollar		<i>38 23</i>			
Standard Dollar.		<i>38 18</i>			
Half Dollar		<i>38 43</i>			
Quarter Dollar ..		<i>38 63</i>			
		<i>38 13</i>			
<i>Average weight</i>		<i>38.387</i>	<i>✓</i>		

M. P. Lawton
Assayer.

6

Treasury Department,

BUREAU OF THE MINT,

Washington, D. C., *Jan 12*, 188*7*.Assayer's Report of Test Coins, issued at the Mint of the
U. S. at *Philadelphia*, in *Oct*, 1886:

DENOMINATION.	No. of Delivery.	WEIGHT.		FINENESS.	
		GRAINS.	DEC.	GOLD.	SILVER.
Double Eagle ...	<i>Delivered 7479</i>	<i>38</i>	<i>69</i>	<i>899</i>	<i>3</i>
Eagle		<i>39</i>	<i>14</i>		
Half Eagle		<i>38</i>	<i>13</i>		
Three Dollars ...		<i>38</i>	<i>62</i>		
Quarter Eagle ...		<i>38</i>	<i>48</i>		
One Dollar		<i>38</i>	<i>47</i>		
Standard Dollar.		<i>38</i>	<i>23</i>		
Half Dollar		<i>38</i>	<i>98</i>		
Quarter Dollar ..		<i>38</i>	<i>88</i>		
Dime		<i>38</i>	<i>73</i>		
<i>Average weight</i>		<i>38.585</i>			

W. P. Lawver

Assayer.

Treasury Department,

BUREAU OF THE MINT,

Washington, D. C., *July 12*, 188*7*.

Assayer's Report of Test Coins, issued at the Mint of the
 U. S. at *Philadelphia*, in *Oct*, 1886:

DENOMINATION.	No. of Delivery.	WEIGHT.		FINENESS.	
		GRAINS.	DEC.	GOLD.	SILVER.
Double Eagle...	<i>Delivered</i>	<i>38</i>	<i>41</i>	<i>899.6</i>	
Eagle		<i>38</i>	<i>71</i>		
Half Eagle.....		<i>38</i>	<i>44</i>		
Three Dollars ...		<i>39</i>	<i>68</i>		
Quarter Eagle...		<i>38</i>	<i>43</i>		
One Dollar.....		<i>38</i>	<i>38</i>		
Standard Dollar.		<i>38</i>	<i>80</i>		
Half Dollar		<i>38</i>	<i>63</i>		
Quarter Dollar ..		<i>38</i>	<i>70</i>		
<i>Average... weight</i>		<i>38.682</i>			

H. P. Lauren

Assayer.

Treasury Dept.
Washington D.C.

January 12. 1887

W. P. Lauer.
Assayer.

Assayer Report of Test-
Coins. Oct. 1886.

Recd January 13. 1887

57 1/2

Treas'y Dept.
Washington. D.C.
Jan'y 12. 1887.

W. P. Lueder.
Cassier.

Report of Test Coins.
Oct. 1886

Recd Jan. 13. 1887

[Abstract:] Transmits Assayer Report upon Special Assay Coins taken from first & two subsequent deliveries October 1886.

W.P.L.

No. 170.

Treasury Department,
Office of the Director of the Mint,
Washington, D.C.,
January 12, 1887

Sir:

I transmit herewith the Assayer's report upon special assay coins taken from the first and two subsequent deliveries in each week at your Mint during the Month of October, 1886, and forwarded for test as prescribed by the Regulations.

The coins were found to be within the legal limits of tolerance.

Very respectfully,
Jas. P. Kimball
Director.

Superintendent Mint U.S.,
At Philadelphia, Pa.

(Ed. 2-21-'81-1,000.)

[Table One:]

1

Treasury Department,
Bureau of the Mint,
Washington, D.C.,
January 12, 1887

Assayer's Report of Test Coins, issued at the Mint of the U.S. at Philadelphia, in Oct., 1886:

Denomination.	No. of Delivery.	Weight. Grains.	Weight. Dec.	Fineness. Gold.		Fineness. Silver.
S.S. Dollars	212	411	80			900.4
	215	412	40			900.1
	217	412	55			900.4
	220	411	95			900.1
	224	412	27			900.4
	227	412	23			900.4
	229	413	05			900.2
	234	412	44			900.1
	236	413	03			899.6
	238	412	57			899.7
	241	412	25			899.9
	244	412	40			900.4
	246	412	67			899.8
Average weight		412	431			
Average fineness						900.11

W.P. Lauren
Assayer.

[Table Two:]

2

Treasury Department,
Bureau of the Mint,
Washington, D.C.,
January 12, 1887

Assayer's Report of Test Coins, issued at the Mint of the U.S. at Philadelphia, in Oct., 1886:

Denomination.	No. of Delivery.	Weight. Grains.	Weight. Dec.	Fineness. Gold.		Fineness. Silver.
Dimes	Delivery 214	38	57			
		38	20			
		38	63			
		38	78			
		38	98			900.2
		38	74			
		38	65			
		38	65			
		40	08			
		39	03			
Average weight		38	831			
			31			

W.P. Lauren
Assayer.

[Table Three:]

3

Treasury Department,
Bureau of the Mint,
Washington, D.C.,
January 12, 1887

Assayer's Report of Test Coins, issued at the Mint of the U.S. at Philadelphia, in Oct., 1886:

Denomination.	No. of Delivery.	Weight. Grains.	Weight. Dec.	Fineness. Gold.		Fineness. Silver.
Dimes	Delivery No. 223	38	22			
		38	60			
		38	33			
		38	75			
		38	02			
		38	48			900.3
		37	78			
		39	03			
		38	48			
		38	55			
Average weight		38	424			

W.P. Lauren
Assayer.

[Table Four:]

4

Treasury Department,
Bureau of the Mint,
Washington, D.C.,
January 12, 1887

Assayer's Report of Test Coins, issued at the Mint of the U.S. at Philadelphia, in Oct., 1886:

Denomination.	No. of Delivery.	Weight. Grains.	Weight. Dec.	Fineness. Gold.		Fineness. Silver.
Dimes	Delivery No. 230	38	36			
		38	28			
		38	72			
		38	38			
		38	53			899.2
		38	23			
		38	18			
		38	43			
		38	63			
		38	13			
Average weight		38	387			

W.P. Lauren
Assayer.

[Table Five:]

6

Treasury Department,
Bureau of the Mint,
Washington, D.C.,
January 12, 1887

Assayer's Report of Test Coins, issued at the Mint of the U.S. at Philadelphia, in Oct., 1886:

Denomination.	No. of Delivery.	Weight. Grains.	Weight. Dec.	Fineness. Gold.		Fineness. Silver.
Dimes	Delivery 247	38	69			
		39	14			
		38	13			
		38	62			
		38	48			
		38	47			899.3
		38	23			
		38	98			
		38	88			
		38	23			
Average weight		38	585			

W.P. Lauren
Assayer.

[Table Six:]

7

Treasury Department,
Bureau of the Mint,
Washington, D.C.,
January 12, 1887

Assayer's Report of Test Coins, issued at the Mint of the U.S. at Philadelphia, in Oct., 1886:

Denomination.	No. of Delivery.	Weight. Grains.	Weight. Dec.	Fineness. Gold.		Fineness. Silver.
Dimes	Delivery -	38	41			
		38	71			
		38	44			
		39	68			
		38	43			899.6
		38	38			
		38	80			
		38	63			
		38	70			
		38	64			
Average weight		38	682			

W.P. Lauren
Assayer.